

Certificate of Test

NE5798

REPORT No.: FNE9336

"Copyright CSIRO 2009 ©"
Copying or alteration of this report
without written authorisation from CSIRO is forbidden.

AS/NZS 1530.3:1999 SIMULTANEOUS DETERMINATION OF IGNITABILITY, FLAME
PROPAGATION, HEAT RELEASE AND SMOKE RELEASE

TRADE NAME: Dektite Red Silicone

SPONSOR: Deks Industries Pty Ltd
841 Mountain Highway
BAYSWATER VIC
AUSTRALIA

DESCRIPTION OF
SAMPLE: The sponsor described the tested specimen as single layered moulded silicone:

Nominal total mass: 3.3 kg/m²
Total thickness: 3.0 mm
Colour: Red

TEST PROCEDURE: Six samples were tested in accordance with Australian Standard 1530, Method for fire tests on building components and structures, Part 3: Simultaneous determination of ignitability, flame propagation, heat release and smoke release, 1999. For the test, each sample was clamped to the specimen holder in four places.

OBSERVATION: Some flashing occurred on the specimens before ignition.

RESULTS: The following means and standard errors were obtained:


Parameter	Mean	Standard Error
Ignition Time (min)	8.0	0.1
Flame Spread Time (s)	45.0	5.7
Heat Release Integral (kJ/m ²)	256.7	42.9
Smoke Release (log ₁₀ D)	0.069	0.103


For regulatory purposes these figures correspond to the following indices:

Ignitability Index (0-20)	Spread of Flame Index (0-10)	Heat Evolved Index (0-10)	Smoke Developed Index (0-10)
12	8	10	8

The results of this fire test may be used to directly assess fire hazard, but it should be recognised that a single test method will not provide a full assessment of fire hazard under all fire conditions.

DATE OF TEST: 18 February 2009
Issued on the 5th day of March 2009 without alterations or additions.


Russell Collins
Testing Officer


Garry E Collins
Manager, Fire Testing and Assessments



This document is issued in accordance with NATA's accreditation requirements.



CSIRO Materials Science and Engineering
14 Julius Avenue, Riverside Corporate Park, North Ryde NSW 2113 AUSTRALIA
Telephone: 61 2 9490 5444 Facsimile: 61 2 9490 5555